



TECHNICAL DATA SHEET



Henkel Canada Corporation
Professional and Consumer Adhesives
Mississauga, ON L5T 3A5
Phone 1-800-624-7767
Fax (440) 937-7067
www.henkel.com www.lepageproducts.com

DESCRIPTION

LePage® Tinted Wood Filler is a quality interior synthetic latex wood filler for cracks, holes and surface imperfections. It is a smooth, buttery paste that spreads and feathers easily. Tinted Wood Filler comes in a variety of pre-tinted colours, which dry to blend with most coloured wood. It can be sanded, stained, painted, varnished, drilled, nailed and screwed. Tinted Wood Filler has a low odour and wet product can be easily cleaned with soap and water.

RECOMMENDED FOR:

Use for filling cracks, scratches and nail holes in wood. It can be used to level wood grain and chipped or gouged surfaces before painting. It can also be used as a filler for drywall and plaster.

NOT RECOMMENDED FOR:

- Areas in contact with water or moisture.
- Use on floors, caulk, sealant or as a joint filler over cracks and joints where expansion and contraction may occur.
- Painted or primed surfaces.
- Use as a skim coat.

FEATURES & BENEFITS:

Feature	Benefits
Variety of pre-tinted colours.....	Blends with most coloured wood
Spreads smoothly.....	Requires only light sanding
Can be painted, stained or varnished....	Blends with surroundings
Can be screwed or nailed.....	Won't crack and crumble from the wood

DIRECTIONS:

Tools Typically Required:

Utility knife, putty knife.

Safety Precautions:

Keep out of reach of children.

Preparation:

Do not use below 10°C (50°F). Surfaces must be clean, dry and free of grease, dust and other contaminants. Do not apply wood filler on painted or primed surfaces. For a light coloured wood, the tinted wood filler may be lightened by pre-mixing with the white tinted wood filler. Experiment with a small sample and compare colour once wood filler is dry. All the tinted wood fillers can be mixed to produce the desired colour. Remove cap and cut at a 45° angle to desired size.



Colour	Item #	Package	Size
White	442193	Squeeze Tube	90 mL
Red Oak	442194	Squeeze Tube	90 mL
Natural	393934	Squeeze Tube	90 mL
Light Oak	393935	Squeeze Tube	90 mL
Teak	393936	Squeeze Tube	90 mL
Walnut	393937	Squeeze Tube	90 mL
Mahogany	393938	Squeeze Tube	90 mL

Application:

Apply with a putty knife, working into cracks and holes. For filling holes deeper than 6 mm (1/4"), apply in layers 2 to 3 mm (1/16" to 1/8"). Allow each layer to dry before applying the next. Best results are obtained by slightly overfilling the final layer above the surface and sanding level again once dry. For sanding, start with 80 grit sandpaper followed by 120 grit. Sand in a circular motion to avoid grooving patch. Paint, stain or varnish once dry. When staining, the wood filler may absorb the stain differently than the surrounding wood. Test a small area first or experiment with a dried sample of wood filler until desired effect is achieved.

Clean-up:

Clean hands and tools immediately with soap and water. Cured filler may be carefully cut away with a sharp-edged tool or sanded.

STORAGE AND DISPOSAL

Damaged by freezing. Store above freezing. Close the tube tightly after each use. Product should not be washed down the drain. To dispose of unwanted product, squeeze out remaining material, allow to dry and discard with trash.

PRECAUTIONS

KEEP OUT OF REACH OF CHILDREN.

Refer to the Material Safety Data Sheet (MSDS) for further information

DISCLAIMER

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Purchasers should test the products to determine acceptable quality and suitability for their own intended use. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

TECHNICAL DATA

Typical Uncured Physical Properties		Typical Application Properties	
<u>Colour:</u>	White, red oak, natural, light oak, teak, walnut, mahogany.	<u>Application Temperature:</u>	Do not use below 10°C (50°F)
<u>Appearance:</u>	Paste	<u>Odour:</u>	Minimal
<u>Base:</u>	Synthetic polymer	<u>Dry Time:</u>	Varies with application thickness, temperature and humidity. A 2 to 3 mm (1/16" to 1/8") depth dries in approximately 4 hours.
<u>Specific Gravity:</u>	1.55		
<u>% Solids:</u>	76 %		
<u>pH:</u>	7.7		
<u>Viscosity:</u>	1200 Mcps @ 1 rpm		
<u>Shelf Life:</u>	18 months from date of manufacture (Unopened)		

Typical Cured Performance Properties

<u>Colour:</u>	White, red oak, natural, light oak, teak, walnut, mahogany.	<u>Service Temperature:</u>	-18°C (0°F) to 66°C (150°F)
----------------	---	-----------------------------	------------------------------